



HENKEL Australia Pty Ltd
A.C.N. 001 302 996
135-141 Canterbury Road
KILSYTH VICTORIA 3164
Tel: (03) 9728 7200
Fax: (03) 9728 5877
Customer Service 1 300 736 777

Distributed by
Solvents Australia Pty Ltd
ABN 74 003 523 117
77 Bassett Street
Mona Vale NSW 2100
PO Box 928 Mona Vale NSW 1660
Tel: (02)9979 6866
Fax: (02)9979 6864

TECHNICAL DATA BULLETIN

ALUMIPREP 33

1. INTRODUCTION

Alumiprep 33 is an acidic metal cleaner and conditioner expressly compounded for aluminium. Prepares aluminium and its alloys for painting or welding. **Alumiprep 33** removes light deposits of oil and grease, mill markings and corrosion products, as well as natural oxide.

Neutralises corrosion inducing materials such as welding or brazing fluxes and perspiration residues.

Effectively removes corrosion products or stains, resulting from weathering, leaves the aluminium surface receptive for additional protection afforded by **Alodine 1000L or 1200L** or clear lacquers or waxes. Maximum protection of aluminium is afforded through the use of **Alumiprep 33** (to clean and brighten), treatment with **Alodine No. 1000L or 1200L** (for corrosion resistance) and the application of clear lacquer or wax.

2. DIRECTIONS FOR USE

Alumiprep 33 is applied by swabbing, spraying or dipping. Follow directions for maximum results.

1. Dilute **Alumiprep 33** with 2 or 3 parts water before using. Use a plastic, porcelain or glass vessel.
2. **Alumiprep 33** is used to clean aluminium windows, doors, railings, etc. If treated in place protect adjacent areas by the use of masking tape and polyethylene sheeting.
3. Freely apply the diluted **Alumiprep 33** solution to the aluminium surface. Flush away the spent **Alumiprep 33** solution with clean water or mop up with damp rags wrung out in clean water.
4. Dry the surface with clean rags or air dry. After drying, treat with **Alodine No. 1000L or 1200L** (for corrosion resistance) apply clear lacquer paints or wax for added protection.

Note: One litre **Alumiprep 33** will, depending on the extent of soil or corrosion, clean approximately 35 square metres.